

Certas Energy UK Ltd.	Chemwatch Hazard Alert Code: 2
Part Number: EAA30 Version No: 1.1	Issue Date: 12/01/2023 Print Date: 12/01/2023
Safety data sheet according to REACH Regulation (EC) No 1907/2006, as amended by UK REACH Regulations SI 2019/758	S.REACH.GB.EN

SECTION 1 Identification of the substance / mixture and of the company / undertaking

1.1. Product Identifier

Product name	HyperDrive Long-Life Antifreeze Concentrate (Purple)				
Synonyms	ot Available				
Other means of identification	UFI:3CUJ-WTVT-4H6W-17HX				

1.2. Relevant identified uses of the substance or mixture and uses advised against

Relevant identified uses	Industrial use, Professional use, Consumer use Antifreeze
Uses advised against	Not Applicable

1.3. Details of the manufacturer or supplier of the safety data sheet

Registered company name	Certas Energy UK Ltd.				
Address	Floor, Allday House, Warrington Road, Birchwood, Warrington, WA3 6GR United Kingdom				
Telephone	0800 685 685				
Fax	ot Available				
Website	Not Available				
Email	HSE.Sharedservice@certasenergy.co.uk				

1.4. Emergency telephone number

	•				
Association / Organisation	Certas Energy UK Ltd.				
Emergency telephone numbers	0330 123 9940 (24 hours, 7days)				
Other emergency telephone numbers	Not Available				

SECTION 2 Hazards identification

2.1. Classification of the substance or mixture

Classified according to GB-CLP Regulation, UK SI 2019/720 and UK SI 2020/1567 [1]	H373 - Specific Target Organ Toxicity - Repeated Exposure Category 2, H302 - Acute Toxicity (Oral) Category 4, H319 - Serious Eye Damage/Eye Irritation Category 2
Legend:	1. Classified by Chemwatch; 2. Classification drawn from GB-CLP Regulation, UK SI 2019/720 and UK SI 2020/1567

2.2. Label elements

Hazard pictogram(s)		
Signal word	Warning	

Hazard statement(s)

. ,						
H373 May cause damage to organs through prolonged or repeated exposure. (Kidneys) (Oral)						
H302	Harmful if swallowed.					
H319	Causes serious eye irritation.					

Supplementary statement(s)

Not Applicable

Precautionary statement(s) Prevention

P260	Do not breathe mist/vapours/spray.				
P264	/ash all exposed external body areas thoroughly after handling.				
P270	Do not eat, drink or smoke when using this product.				
P280	Wear protective gloves, protective clothing, eye protection and face protection.				

Precautionary statement(s) Response

P305+P351+P338	IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.				
P314	Get medical advice/attention if you feel unwell.				
P337+P313	If eye irritation persists: Get medical advice/attention.				
P301+P312	IF SWALLOWED: Call a POISON CENTER/doctor/physician/first aider if you feel unwell.				
P330	P330 Rinse mouth.				

Precautionary statement(s) Storage

Not Applicable

Precautionary statement(s) Disposal

P501	Dispose of contents/container to authorised hazardous or special waste collection point in accordance with any local regulation.
P301	Dispose of contents/container to authorised nazardous of special waste collection point in accordance with any local regulation.

2.3. Other hazards

May produce skin discomfort*.

REACH - Art.57-59: The mixture does not contain Substances of Very High Concern (SVHC) at the SDS print date.

SECTION 3 Composition / information on ingredients

3.1.Substances

See 'Composition on ingredients' in Section 3.2

3.2.Mixtures

1.CAS No 2.EC No 3.Index No 4.REACH No	%[weight]	Name	Classified according to GB-CLP Regulation, UK SI 2019/720 and UK SI 2020/1567	SCL / M-Factor	Nanoform Particle Characteristics
1.107-21-1* 2.203-473-3 3.603-027-00-1 4.Not Available	>90-<100	ethylene glycol *	Specific Target Organ Toxicity - Repeated Exposure Category 2, Acute Toxicity (Oral) Category 4; H373, H302 ^[1]	Not Available	Not Available
1.3164-85-0* 2.221-625-7 3.Not Available 4.Not Available	1-3	potassium 2-ethylhexanoate	Reproductive Toxicity Category 2, Serious Eye Damage/Eye Irritation Category 1, Skin Corrosion/Irritation Category 2; H361d, H318, H315 ^[1]	Not Available	Not Available
Legend:	Legend: 1. Classified by Chemwatch; 2. Classification drawn from GB-CLP Regulation, UK SI 2019/720 and UK SI 2020/1567; 3. Classification drawn from C&L * EU IOELVs available; [e] Substance identified as having endocrine disrupting properties				. Classification drawn

SECTION 4 First aid measures

4.1. Description of first aid measures

Eye Contact	 If this product comes in contact with the eyes: Wash out immediately with fresh running water. Ensure complete irrigation of the eye by keeping eyelids apart and away from eye and moving the eyelids by occasionally lifting the upper and lower lids. Seek medical attention without delay; if pain persists or recurs seek medical attention. Removal of contact lenses after an eye injury should only be undertaken by skilled personnel.
Skin Contact	If skin contact occurs: Immediately remove all contaminated clothing, including footwear. Flush skin and hair with running water (and soap if available). Seek medical attention in event of irritation.
Inhalation	 If fumes, aerosols or combustion products are inhaled remove from contaminated area. Other measures are usually unnecessary.
Ingestion	 Immediately give a glass of water. First aid is not generally required. If in doubt, contact a Poisons Information Centre or a doctor.

4.2 Most important symptoms and effects, both acute and delayed

See Section 11

4.3. Indication of any immediate medical attention and special treatment needed

Treat symptomatically.

SECTION 5 Firefighting measures

5.1. Extinguishing media

- Water spray or fog.
- Foam.
- Dry chemical powder.
 BCF (where regulations permit).
- Carbon dioxide.

5.2. Special hazards arising from the substrate or mixture

Fire Incompatibility	None known.		
5.3. Advice for firefighters			
Fire Fighting	 Alert Fire Brigade and tell them location and nature of hazard. Wear full body protective clothing with breathing apparatus. Prevent, by any means available, spillage from entering drains or water course. Use water delivered as a fine spray to control fire and cool adjacent area. Avoid spraying water onto liquid pools. DO NOT approach containers suspected to be hot. Cool fire exposed containers with water spray from a protected location. If safe to do so, remove containers from path of fire. 		
Fire/Explosion Hazard	 Combustible. Slight fire hazard when exposed to heat or flame. Heating may cause expansion or decomposition leading to violent rupture of containers. On combustion, may emit irritating/ toxic fumes. May emit acrid smoke. Mists containing combustible materials may be explosive. May emit poisonous fumes. May emit corrosive fumes. 		

SECTION 6 Accidental release measures

6.1. Personal precautions, protective equipment and emergency procedures

See section 8

6.2. Environmental precautions

See section 12

6.3. Methods and material for containment and cleaning up

Minor Spills	 Remove all ignition sources. Clean up all spills immediately. Avoid breathing vapours and contact with skin and eyes. Control personal contact with the substance, by using protective equipment. Contain and absorb spill with sand, earth, inert material or vermiculite. Wipe up. Place in a suitable, labelled container for waste disposal.
Major Spills	 Moderate hazard. Clear area of personnel and move upwind. Alert Fire Brigade and tell them location and nature of hazard. Wear breathing apparatus plus protective gloves. Prevent, by any means available, spillage from entering drains or water course. No smoking, naked lights or ignition sources. Increase ventilation. Stop leak if safe to do so. Contain spill with sand, earth or vermiculite. Collect recoverable product into labelled containers for recycling. Absorb remaining product with sand, earth or vermiculite. Collect solid residues and seal in labelled drums for disposal. Wash area and prevent runoff into drains. If contamination of drains or waterways occurs, advise emergency services.

6.4. Reference to other sections

Personal Protective Equipment advice is contained in Section 8 of the SDS.

SECTION 7 Handling and storage

7.1. Precautions for safe handling

- Safe handling
- Avoid all personal contact, including inhalation.
- Wear protective clothing when risk of exposure occurs.
 - Use in a well-ventilated area.

	 Prevent concentration in hollows and sumps. DO NOT enter confined spaces until atmosphere has been checked. Avoid smoking, naked lights or ignition sources. Avoid contact with incompatible materials. When handling, DO NOT eat, drink or smoke. Keep containers securely sealed when not in use. Avoid physical damage to containers. Always wash hands with soap and water after handling. Work clothes should be laundered separately. Use good occupational work practice. Observe manufacturer's storage and handling recommendations contained within this SDS.
	 Atmosphere should be regularly checked against established exposure standards to ensure safe working conditions. DO NOT allow clothing wet with material to stay in contact with skin
Fire and explosion protection	See section 5
Other information	 Consider storage under inert gas. Material is hygroscopic, i.e. absorbs moisture from the air. Keep containers well sealed in storage. Store in original containers. Keep containers securely sealed. No smoking, naked lights or ignition sources. Store in a cool, dry, well-ventilated area. Store away from incompatible materials and foodstuff containers. Protect containers against physical damage and check regularly for leaks. Observe manufacturer's storage and handling recommendations contained within this SDS.

7.2. Conditions for safe storage, including any incompatibilities

Suitable container	 Metal can or drum Packaging as recommended by manufacturer. Check all containers are clearly labelled and free from leaks.
Storage incompatibility	None known
Hazard categories in accordance with Regulation (EC) No 1272/2008	Not Available
Qualifying quantity (tonnes) of dangerous substances as referred to in Article 3(10) for the application of	Not Available

7.3. Specific end use(s)

See section 1.2

SECTION 8 Exposure controls / personal protection

8.1. Control parameters

Ingredient	DNELs Exposure Pattern Worker	PNECs Compartment	
ethylene glycol	Dermal 3 mg/kg bw/day (Systemic, Chronic) Inhalation 35.3 mg/m ³ (Systemic, Chronic) Inhalation 9 mg/m ³ (Local, Chronic) Dermal 15 mg/kg bw/day (Systemic, Acute) Inhalation 176.5 mg/m ³ (Local, Acute) Dermal 53 mg/kg bw/day (Systemic, Chronic) * Inhalation 7 mg/m ³ (Local, Chronic) *	10 mg/L (Water (Fresh)) 1 mg/L (Water - Intermittent release) 10 mg/L (Water (Marine)) 37 mg/kg sediment dw (Sediment (Fresh Water)) 3.7 mg/kg sediment dw (Sediment (Marine)) 1.53 mg/kg soil dw (Soil) 199.5 mg/L (STP)	
Dermal 5.95 mg/kg bw/day (Systemic, Chronic) Inhalation 32 mg/m ³ (Systemic, Chronic) Dermal 2.98 mg/kg bw/day (Systemic, Chronic) * Inhalation 8 mg/m ³ (Systemic, Chronic) * Oral 2.5 mg/kg bw/day (Systemic, Chronic) *		0.36 mg/L (Water (Fresh)) 0.036 mg/L (Water - Intermittent release) 0.493 mg/L (Water (Marine)) 6.37 mg/kg sediment dw (Sediment (Fresh Water)) 0.637 mg/kg sediment dw (Sediment (Marine)) 1.06 mg/kg soil dw (Soil) 71.7 mg/L (STP)	

* Values for General Population

Occupational Exposure Limits (OEL)

INGREDIENT DATA Ingredient STEL Peak Source Material name TWA Notes UK Workplace Exposure Limits ethylene glycol Ethane-1,2-diol: vapour 20 ppm / 52 mg/m3 104 mg/m3 / 40 ppm Not Available Sk (WELs). UK Workplace Exposure Limits Not Available ethylene glycol Ethane-1,2-diol: particulate 10 mg/m3 Not Available Sk (WELs).

Emergency Limits				
Ingredient	TEEL-1	TEEL-2	TEEL-3	
ethylene glycol	30 ppm	150 ppm	900 ppm	

art Number: EAA30	Page 5 of 14			Issue Date: 12/01/202	
ersion No: 1.1	HyperDrive Long-Life Antifreeze Concentrate (Purple)			Print Date: 12/01/20	
Ingredient	Original IDLH	Revised IDLH			
ethylene glycol	Not Available	Not Available			
potassium 2-ethylhexanoate	Not Available	Not Available			
Occupational Exposure Banding					
Ingredient	Occupational Exposure Band Rating	Occupational	Exposure Band Limit		
potassium 2-ethylhexanoate	E	≤ 0.01 mg/m³	•		
Notes:	Occupational exposure banding is a process of assigning chemicals into specific categories or bands based on a chemical's potency and the adverse health outcomes associated with exposure. The output of this process is an occupational exposure band (OEB), which corresponds to a range of exposure concentrations that are expected to protect worker health.				
3.2. Exposure controls					
	The basic types of engineering controls are: Process controls which involve changing the way a job acti Enclosure and/or isolation of emission source which keeps "adds" and "removes" air in the work environment. Ventilat ventilation system must match the particular process and o Employers may need to use multiple types of controls to pr General exhaust is adequate under normal operating cond overexposure exists, wear approved respirator. Correct fit or closed storage areas. Air contaminants generated in the velocities" of fresh circulating air required to effectively rem	a selected hazard "physically" av ion can remove or dilute an air co chemical or contaminant in use. revent employee overexposure. itions. Local exhaust ventilation n is essential to obtain adequate pr workplace possess varying "esc	vay from the worker and ven ntaminant if designed proper nay be required in specific cir otection. Provide adequate v	rly. The design of a rcumstances. If risk of entilation in warehouse	
	Type of Contaminant:		Air Speed:		
	solvent, vapours, degreasing etc., evaporating from tank (in still air).			0.25-0.5 m/s (50-100 f/min)	
	aerosols, fumes from pouring operations, intermittent container filling, low speed conveyer transfers, welding, spray drift, plating acid fumes, pickling (released at low velocity into zone of active generation)			0.5-1 m/s (100-200 f/min.)	
8.2.1. Appropriate engineering controls	direct spray, spray painting in shallow booths, drum filling, conveyer loading, crusher dusts, gas discharge (active generation into zone of rapid air motion)			1-2.5 m/s (200-500 f/min.)	
	grinding, abrasive blasting, tumbling, high speed wheel generated dusts (released at high initial velocity into zone of very high rapid air motion).			2.5-10 m/s (500-2000 f/min.)	
	Within each range the appropriate value depends on:				
	Lower end of the range	Upper end of the range			
	1: Room air currents minimal or favourable to capture	1: Disturbing room air currents	_		
	2: Contaminants of low toxicity or of nuisance value only.	2: Contaminants of high toxicity			
	3: Intermittent, low production.	3: High production, heavy use			
	4: Large hood or large air mass in motion	4: Small hood-local control only			
	Simple theory shows that air velocity falls rapidly with dista with the square of distance from the extraction point (in sin accordingly, after reference to distance from the contamina 1-2 m/s (200-400 f/min) for extraction of solvents generate producing performance deficits within the extraction appara more when extraction systems are installed or used.	nple cases). Therefore the air spe ting source. The air velocity at th d in a tank 2 meters distant from t	ed at the extraction point sho e extraction fan, for example he extraction point. Other mo	buld be adjusted, , should be a minimum of echanical considerations,	
8.2.2. Personal protection					
Eye and face protection	 Safety glasses with side shields. Chemical goggles. Contact lenses may pose a special hazard; soft contact the wearing of lenses or restrictions on use, should be and adsorption for the class of chemicals in use and at their removal and suitable equipment should be readily 	created for each workplace or tain account of injury experience. M	sk. This should include a revi edical and first-aid personne	iew of lens absorption I should be trained in	

remove contact lens as soon as practicable. Lens should be removed at the first signs of eye redness or irritation - lens should be removed in a clean environment only after workers have washed hands thoroughly. [CDC NIOSH Current Intelligence Bulletin 59], [AS/NZS 1336 or national equivalent] Skin protection See Hand protection below Wear chemical protective gloves, e.g. PVC.
Wear safety footwear or safety gumboots, e.g. Rubber The selection of suitable gloves does not only depend on the material, but also on further marks of quality which vary from manufacturer to manufacturer. Where the chemical is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. The exact break through time for substances has to be obtained from the manufacturer of the protective gloves and has to be observed when Hands/feet protection making a final choice. Personal hygiene is a key element of effective hand care. Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Suitability and durability of glove type is dependent on usage. Important factors in the selection of gloves include: · frequency and duration of contact,

 ejove thickness and ejevetitity Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, ASINZS 2161.1 or national equivalent). When protocing of or frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, ASINZS 2161.10.1 or national equivalent) is recommended. When only brief contact is expected, a glove with a protection class of 5 or higher (breakthrough time greater than 60 minutes according to EN 374, ASINZS 2161.10.1 or national equivalent) is recommended. Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use. Conteminated gloves should be replaced. As defined in ASTM F-739-96 in any application, gloves are rated as: Excellent when breakthrough time > 20 min Good when breakthrough time > 20 min For or when glove material degrades For general applications, gloves with a thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove with e activation of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely by esh of the advity being conducted, glovee of varying thickness may be required for specific tasks. For example:		chemical resistance of glove material,		
Select goves tested to a relevant standard (e.g. Europe EN 374, US F739, ASNX2 2161.1 or national equivalent). • When prolonged or frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, ASNX25 2161.1.0.1 or national equivalent) is recommended. • When only brief CN 374, ASNX25 2161.1.0.1 or national equivalent) is recommended. • When only brief CN 374, ASNX25 2161.0.1 or national equivalent) is recommended. • Ontaminate gloves should be replaced. • Contaminate gloves should be taken into account when considering gloves for long-term use. • Excellent when breakthrough time > 480 min • Some glove pontery pass are allowed with a protection of glove resistance to a specific chemical, as the permeation efficiency of the placed. • Poor when breakthrough time > 400 min • Some glove ponterised gloves with a thickness typically greater than 0.35 mm, are recommended. • Fair when breakthrough time > 400 min • Some glove ponterised gloves with a thickness typically greater than 0.35 mm, are recommended. • Fair when breakthrough time > 400 min • Some glove ponterised gloves with a thickness typically greater than 0.35 mm, are recommended. • For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should also be based on consideration of the glove time should also be based on consideration of the task requirements and knowing its accoming the glove time task. • For general applications, gloves with a bioknese striptical where a high degree din anuladextriptis preceded. How				
• When protouged or frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, AS/N2S 2161.10.1 or national equivalent) is recommended. • When only brief contact is expected, a glove with a protection of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, AS/N2S 2161.10.1 or national equivalent) is recommended. • Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use. • Contaminated gloves should be replaced. • As defined in ASTM F7-339-68 in any application, gloves are rated as: • Excellent when breakthrough time > 20 min • Fair when breakthrough time > 20 min • Fair when breakthrough time > 20 min • Fair when breakthrough time > 20 min • For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Clove thickness may also vary depending on the glove multacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of		· dexterity		
minutes according to EN 374, AS/NZS 2161:0.1 or national equivalent) is recommended. When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, AS/NZS 2161:10.1 or national equivalent) is recommended. Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use. Contaminated gloves should be replaced. As defined in ASTM F-73.99 in any application, gloves are rated as: Excellent when breakthrough time > 20 min Good when breakthrough time > 20 min From when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasized that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the tasks. For example: Thinner gloves (bow to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thiner gloves (bur to 0.1 mm or less) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential. Gloves must only be worn on clean hands. After using glove		Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, AS/NZS 2161.1 or national equivalent).		
• When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, AS/NZ5 2161.10.1 or national equivalent) is recommended. • Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use. • Contaminated gloves should be replaced. As defined in ASTM F-739-96 in any application, gloves are rated as: • Excellent when breakthrough time > 20 min • Fair when breakthrough time > 20 min • Fair when breakthrough time > 20 min • Poor when glove material digrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove for specific tasks. For example: • Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dextriry is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. • Diver spotential See Other protection below • Diver single protection below • Overalls. • Diver single protection below • Overalls. • Diver single protection below • Overalls. • Diver protection • Diverall		· When prolonged or frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 240		
374, AS/AZS 2161.10.1 or national equivalent) is recommended. • Some glove polymer types are less alfected by movement and this should be taken into account when considering gloves for long-term use. • Contaminated gloves should be replaced. As defined in ASTM F-739-96 in any application, gloves are rated as: • Excellent when breakthrough time > 400 min • Good when breakthrough time > 20 min • Fair when breakthrough time > 20 min • Poor when glove material degrades For general applications, gloves is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the exact composition of the glove material. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most apportinte glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: • Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexiently is needed. However, these gloves are only likely to give should hor bus tor duration protection and would normally be just for single use applications, then disposed of. • Thinner gloves (up to 0.1 mm or less) may be required where a high degree of manual dexiently is needed. However, these gloves are only likely to give should beve and the durat		minutes according to EN 374, AS/NZS 2161.10.1 or national equivalent) is recommended.		
 Contaminated gloves should be replaced. As defined in ASTM F-739-96 in any application, gloves are rated as: Excellent when breakthrough time > 20 min Good when breakthrough time > 20 min Fair when breakthrough time > 20 min Fair when breakthrough time > 20 min Foor when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove maturfail. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove so traying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterily is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. P.V.C apron. P.V.C apron. P.V.C apron. Skin cleansing cream. Skin cleansing cream. 				
As defined in ASTM F-739-96 in any application, gloves are rated as: • Excellent when breakthrough time > 400 min • Good when breakthrough time > 20 min • Fair when breakthrough time > 20 min • For when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required thorse gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. • Thinker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Glove thickness See Other protection below • Overalls. • Overalls. • P.VC apron. • Norealls. • P.VC apron. • Skin cleansing cream. • Skin cleansing cream				
 Excellent when breakthrough time > 480 min Good when breakthrough time > 20 min Good when breakthrough time > 20 min Poor when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. For example: Thinker gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where a high degree of manual dexter if is in eeded. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where a high degree of manual dexter file. However, these gloves are only likely to give smut on the annotacturer, the glove the set as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Doveralls. P.V.C apron. P.V.C apron. Skin cleansing cream		5 I		
 Good when breakthrough time > 20 min Fair when breakthrough time < 20 min For when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (up to 3 mn or more) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mn or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Poveralls. P.VC apron. Barrier cream. Skin cleansing cream. 				
 Fair when breakthrough time < 20 min Poor when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Other protection See Other protection below P.V.C apron. P.V.C apron. Skin cleansing cream. Skin cleansing cream. 				
 Poor when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual deterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thinker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Body protection See Other protection below P.V.C apron. P.V.C apron. P.V.C apron. Skin cleansing cream. Skin cleansing cream. 		•		
For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: • Thinnen gloves (down to 0.1 mm or less) may be required where a high degree of manual dextrity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. • Thinker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Glove smust only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Body protection See Other protection below • Overalls. • Overalls. • P.V.C apron. • Sin cleansing cream. • Skin cleansing cream. • Skin cleansing cream.		0		
It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation of fifciency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may also vary depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Body protection See Other protection below P.V.C. apron. Barrier cream. Skin cleansing cream. Skin cleansing cream.		5 5 F		
efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thinker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Body protection See Other protection below * Overalls. • Overalls. • P.V.C apron. • Barrier cream. • Skin cleansing cream. • Skin cleansing cream.				
consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: • Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. • Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Body protection See Other protection below • Overalls. • Overalls. • P.V.C apron. • Barrier cream. • Skin cleansing cream. • Skin cleansing cream.				
Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Body protection Other protection below P.V.C apron. Barrier cream. Skin cleansing cream. Skin cleansing cream. 				
data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Body protection See Other protection below Other protection Barrier cream. Skin cleansing cream. 				
Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Body protection See Other protection below Other protection P.V.C apron. Barrier cream. Skin cleansing cream. 				
 Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Body protection See Other protection below Other protection Barrier cream. Skin cleansing cream. 				
likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Body protection See Other protection below • Overalls. • Overalls. • P.V.C apron. • Barrier cream. • Skin cleansing cream.				
puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Body protection See Other protection below Other protection Overalls. P.V.C apron. Barrier cream. Skin cleansing cream. Skin cleansing cream. 				
Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Body protection See Other protection below Other protection • Overalls. • P.V.C apron. • Barrier cream. • Skin cleansing cream.		• Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or		
Body protection See Other protection below Other protection P.V.C apron. Barrier cream. Skin cleansing cream. Skin cleans				
Body protection See Other protection below Other protection • Overalls. • Barrier cream. • Skin cleansing cream.				
Other protection P.V.C apron. Barrier cream. Skin cleansing cream. 		moisturiser is recommended.		
Other protection P.V.C apron. Barrier cream. Skin cleansing cream. 	Body protection	See Other protection below		
Other protection P.V.C apron. Barrier cream. Skin cleansing cream. 		h Ourselle		
Other protection • Barrier cream. • Skin cleansing cream.				
 Skin cleansing cream. 	Other protection			
	Other protection			
Lye wash unit.		5		
		· Eye wash unit.		

Recommended material(s)

GLOVE SELECTION INDEX

Glove selection is based on a modified presentation of the:

"Forsberg Clothing Performance Index". The effect(s) of the following substance(s) are taken into account in the *computer-generated* selection:

HyperDrive Long-Life Antifreeze Concentrate (Purple)

Material	CPI
NATURAL RUBBER	A
NATURAL+NEOPRENE	A
NEOPRENE	A
NEOPRENE/NATURAL	A
NITRILE	A
NITRILE+PVC	A
PE/EVAL/PE	A
PVC	A
TEFLON	A
PVA	В

* CPI - Chemwatch Performance Index

A: Best Selection

B: Satisfactory; may degrade after 4 hours continuous immersion

C: Poor to Dangerous Choice for other than short term immersion

NOTE: As a series of factors will influence the actual performance of the glove, a final selection must be based on detailed observation. -

* Where the glove is to be used on a short term, casual or infrequent basis, factors such as "feel" or convenience (e.g. disposability), may dictate a choice of gloves which might otherwise be unsuitable following long-term or frequent use. A qualified practitioner should be consulted.

8.2.3. Environmental exposure controls

See section 12

SECTION 9 Physical and chemical properties

9.1. Information on basic physical and chemical properties

Appearance	Purple Liquid		
Physical state	Liquid	Relative density (Water = 1)	1.12 (20 °C)
Odour	Not Available	Partition coefficient n-octanol / water	-1.93
Odour threshold	Not Available	Auto-ignition temperature (°C)	>400

pH (as supplied)	7.5-9	Decomposition temperature (°C)	Not Available
Melting point / freezing point (°C)	-12	Viscosity (cSt)	21 @ 20
Initial boiling point and boiling range (°C)	>170	Molecular weight (g/mol)	Not Available
Flash point (°C)	>111	Taste	Not Available
Evaporation rate	Not Available BuAC = 1	Explosive properties	Not Available
Flammability	Not Applicable	Oxidising properties	Not Available
Upper Explosive Limit (%)	Not Available	Surface Tension (dyn/cm or mN/m)	Not Available
Lower Explosive Limit (%)	Not Available	Volatile Component (%vol)	Not Available
Vapour pressure (kPa)	0,06 mmHg (20 °C)	Gas group	Not Available
Solubility in water	Miscible	pH as a solution (1%)	Not Available
Vapour density (Air = 1)	2.1	VOC g/L	Not Available
Nanoform Solubility	Not Available	Nanoform Particle Characteristics	Not Available
Particle Size	Not Available		

9.2. Other information

Not Available

SECTION 10 Stability and reactivity

10.1.Reactivity	See section 7.2
10.2. Chemical stability	 Unstable in the presence of incompatible materials. Product is considered stable. Hazardous polymerisation will not occur.
10.3. Possibility of hazardous reactions	See section 7.2
10.4. Conditions to avoid	See section 7.2
10.5. Incompatible materials	See section 7.2
10.6. Hazardous decomposition products	See section 5.3

SECTION 11 Toxicological information

11.1. Information on toxicological effects

Inhaled	The material is not thought to produce adverse health effects or irritation of the respiratory tract (as classified by EC Directives using animal models). Nevertheless, good hygiene practice requires that exposure be kept to a minimum and that suitable control measures be used in an occupational setting.			
Ingestion	The material has NOT been classified by EC Directives or other classification systems as "harmful by ingestion". This is because of the lack of corroborating animal or human evidence.			
Skin Contact	Skin contact is not thought to have harmful health effects (as classified under EC Directives); the material may still produce health damage following entry through wounds, lesions or abrasions. There is some evidence to suggest that this material can cause inflammation of the skin on contact in some persons. Open cuts, abraded or irritated skin should not be exposed to this material Entry into the blood-stream, through, for example, cuts, abrasions or lesions, may produce systemic injury with harmful effects. Examine the skin prior to the use of the material and ensure that any external damage is suitably protected.			
Eye	This material can cause eye irritation and damage in some persons.			
Chronic	Ample evidence from experiments exists that there is a suspicion this material directly reduces fertility.			
HyperDrive Long-Life	τοχιζιτγ	IRRITATION		
Antifreeze Concentrate (Purple)	Not Available	Not Available		
	тохісіту	IRRITATION		
ethylene glycol	Dermal (rabbit) LD50: 9530 mg/kg ^[2]	Eye (rabbit): 100 mg/1h - mild		
	Inhalation (Human) TCLo: 10000 mg/m3 ^[2]	Eye (rabbit): 12 mg/m3/3D		

	Inhalation(Rat) LC50: 50100 mg/m3/8 hr ^[2]	Eye (rabbit): 1440mg/6h-moderate	
	Oral (child) TDLo: 5500 mg/kg ^[2]	Eye (rabbit): 500 mg/24h - mild	
	Oral (Human)LDLo: 398 mg/kg ^[2]	Eye: no adverse effect observed (not irritating) ^[1]	
	Oral (Rat) LD50; 4700 mg/kg ^[2]	Skin (rabbit): 555 mg(open)-mild	
		Skin: no adverse effect observed (not irritating) ^[1]	
potassium 2-ethylhexanoate	TOXICITY		
	dermal (rat) LD50: >2000 mg/kg ^[1]	Not Available	
. , , , , , , , , , , , , , , , , , , ,	Oral (Rat) LD50; 2043 mg/kg ^[1]		

	specified data extracted from RTECS - Register of Toxic Effect of chemical Substances
ethylene glycol	[Estimated Lethal Dose (human) 100 m!; RTECS quoted by Orical Substance is reproductive effector in rats (birth defects). Mutagenic to rat cells. For ethylene glycol: Ethylene glycol is quickly and extensively absorbed throughout the gastrointestinal tract. Limited information suggests that it is also absorbed through the airways; absorption through skin is apparently slow. Following absorption, it is distributed throughout the body. In humans, it is initially metabolized by alcohol dehydrogenase to form glycoladehydw, which is rapid/v converted to glycolic acid and glycoxi. These breakdown products are oxidized to glycolytate, which may be further metabolized to formic acid, cvalic acid, and glycoin. Breakdown of both glycine and formic acid an generate carbon dioxide, which is one of the major elimination products of ehylene glycol. In addition to exhalet carbon dioxide, ehylene glycol is eliminated in the urine as both the parent corporate 12:24 hours after swallowing sufficient amounts of ethylene glycol. Symptoms include hyperventilation, shallow rapid breathing, and generalized swelling of the lungs with acidium oxalate deposits occasionally appearing in the lungs. Respiratory system involvement appears to be dose-dependent and occurs at the same time as calcivascular changes. Later, there poisoning. Cardiovascular effects: Cardiovascular system involvement in humans occurs at the same time as respiratory system involvement, during the second phase of ethylene glycol poisoning by swallowing, which is 12:24 hours after acute exposure. The symptoms of poisoning involving the near include hyge end glycol poisoning by swallowing, which is 12:24 hours after surgery, deposition of oxalate crystals was shorn to have occurred. Musculoskelatal effects: Cardiovascular system involvement in uncars, acute exposure to high levels of ethylene glycol can cause serious cardiogenic shock. In lethal cases, inflammation of the heart muscle has been observed at autopsy. Cardiovascular involvement appears to be are and usuall
potassium 2-ethylhexanoate	No significant acute toxicological data identified in literature search. For aliphatic fatty acids (and salts) Acute oral (gavage) toxicity: The acute oral LD50 values in rats for both were greater than >2000 mg/kg bw Clinical signs were generally associated with poor condition following administration of high doses (salivation, diarrhoea, staining, piloerection and lethargy). There were no adverse effects on body weight in any study In some studies, excess test substance and/or irritation in the gastrointestinal tract was observed at necropsy. Skin and eye irritation potential, with a few stated exceptions, is chain length dependent and decreases with increasing chain length According to several OECD test regimes the animal skin irritation studies indicate that the C6-10 aliphatic acids are severely irritating or corrosive, while the C12 aliphatic acid is irritating, and the C14-22 aliphatic acids generally are not irritating or mildly irritating. Human skin irritation studies using more realistic exposures (30-minute,1-hour or 24-hours) indicate that the aliphatic acids have sufficient, good or very good skin compatibility.
	Animal eye irritation studies indicate that among the aliphatic acids, the C8-12 aliphatic acids are irritating to the eye while the C14-22 aliphatic acids are not irritating. Eye irritation potential of the ammonium salts does not follow chain length dependence; the C18 ammonium salts are corrosive to the eyes. Dermal absorption: The in vitro penetration of C10, C12, C14, C16 and C18 fatty acids (as sodium salt solutions) through rat skin decreases with increasing chain

length. At 86.73 ug C16/cm2 and 91.84 ug C18/cm2, about 0.23% and less than 0.1% of the C16 and C18 soap solutions is absorbed after 24 h exposure, respectively. Sensitisation:

No sensitisation data were located.

	Repeat dose toxicity:	and a state of the second state of the second state of the	
	Repeated dose oral (gavage or diet) exposure to aliph 1000 mg/kg bw.	atic acids did not result in systemic to	kicity with NOAELS greater than the limit dose of
	Mutagenicity		
	Aliphatic acids do not appear to be mutagenic or clast Carcinogenicity	ogenic in vitro or in vivo	
	No data were located for carcinogenicity of aliphatic fa	tty acids.	
	Reproductive toxicity		
	No effects on fertility or on reproductive organs, or dev correspond to the maximum dose tested. The weight of aliphatic acids category.		
	Given the large number of substances in this category and similarity of toxicokinetic properties, both mamma and selecting the most conservative supporting substa	lian and aquatic endpoints were filled ince effect level.	using read-across to the closest structural analogue,
	Structure-activity relationships are not evident for the r substances limits the ability to discern structural effect conservative effect value was selected for read across	s on biological activity. Regardless, th	e closest structural analogue with the most
	Metabolism:		
	The aliphatic acids share a common degradation path systems. Common biological pathways result in struct responsible for similar environmental behavior and es	urally similar breakdown products, and	are, together with the physico-chemical properties,
	Differences in metabolism or biodegradability of even expected; even-and odd-numbered carbon chain com	and odd numbered carbon chain com	oounds or saturated/ unsaturated compounds are not
	expected to be metabolized and biodegraded in the sa		
	The acid and alkali salt forms of the homologous aliph		
	when they become bioavailable; therefore,data read a and vice versa. In the gastrointestinal tract, acids and facilitated diffusion. It is expected that both the acids a that for both aliphatic acid or aliphatic acid salt,the san	bases are absorbed in the undissocia nd the salts will be present in (or conv	ted (non-ionised) form by simple diffusion or by rerted to) the acid form in the stomach. This means
	increased pH, will shift towards dissociation (ionised for	orm).	· · ·
	Hence, the situation will be similar for compounds orig Note that the saturation or unsaturation level is not a fa	-	
	process		s and is not a childer component of the read across
	Toxicokinetics: The turnover of the [14C] surfactants in the rat showed intraperitoneal or subcutaneous administration. The m remaining material was incorporated in the body. Long mg/kg bw, 71% of the C16:0 and 56% of the C18:0 wa	ain route of excretion was as 14CO2 i er fatty acid chains are more readily in	n the expired air at 6 h after administration. The norporated than shorter chains. At ca. 1.55 and 1.64
	Glycidyl fatty acid esters (GEs), one of the main conta process of edible oils and therefore occur in almost all		
	hydrolyze into the free form glycidol in the gastrointest		
	significant effort has been devoted to inhibit and elimin		This class of compounds has been reported in edible
	GEs contain a common terminal epoxide group but ex oils after overestimation of 3-monochloropropane-1,2-		
	studied as food processing contaminants and are four 3-Monochloropropane-1,2-diol (3-MCPD) and 2-mono	71 0	
	propanetriol). 3- and 2-MCPD and their fatty acid ester decomposition of 3- and 2-MCPD. It forms monoester: HVP during the hydrochloric acid-mediated hydrolysis	s with fatty acids (GE) during the refin	ng of vegetable oils. Chloropropanols are formed in
	reaction of endogenous or added chloride with glycerc	l or acylglycerol.	
	Although harmful effects on humans and animals have been identified as rodent genotoxic carcinogens, ultim sites (glycidol). Therefore, 3-MCPD and glycidol have t	ately resulting in the formation of kidn	ey tumours (3-MCPD) and tumours at other tissue
	to humans (group 2A), respectively, by the Internation	al Agency for Research on Cancer (IA	RC).
	Diacylglyceride (DAG) based oils produced by one cor Several reports have also suggested that a bidirection	al transformation process may occur i	not only between glycidol and 3-MCPD but also their
	esterified forms in the presence of chloride ions. The t acidic conditions in the presence of chloride ion.	ransformation rate of glycidol to 3-MC	PD was higher than that of 3-MCPD to glycidol under
	Precursors of GEs in refined oils have been identified they also originate from triacylglycerides (TAGs) is still	a topic of controversial debates. Seve	eral authors noted that pure TAGs were stable during
	heat treatment (such as 235 deg C) for 3 h and were t that small amounts of GEs are present in a heat-treate attributed to the pyrolysis of TAGs to DAGs and MAGs	ed oil model consisting of almost 100%	TAGs. The formation of GEs from TAGs can be
	mechanism for the formation of GE intermediates and	the relationship between GEs and 3-1	ICPD esters are still unknown.
	Fatty acid salts of low acute toxicity. Their potential to	irritate the skin and eyes is dependen	on chain length.
Acute Toxicity	×	Carcinogenicity	×
Skin Irritation/Corrosion	×	Reproductivity	×
Serious Eve Damage/Irritation	· · · · · · · · · · · · · · · · · · ·	STOT - Single Exposure	×

Acute loxicity	•	Carcinogenicity	^
Skin Irritation/Corrosion	×	Reproductivity	×
Serious Eye Damage/Irritation	×	STOT - Single Exposure	×
Respiratory or Skin sensitisation	×	STOT - Repeated Exposure	*
Mutagenicity	×	Aspiration Hazard	×

Legend:

Data either not available or does not fill the criteria for classification
 Data available to make classification

11.2 Information on other hazards

11.2.1. Endocrine Disruption Properties Not Available

11.2.2. Other Information See Section 11.1

SECTION 12 Ecological information

HyperDrive Long-Life Antifreeze Concentrate (Purple)	Endpoint	Test Duration (hr)	Species		Value	Source
	Not Available	Not Available	Not Available		Not Available	Not Availabl
	Endpoint	Test Duration (hr)	Species	Valu	ie	Sourc
	EC50(ECx)	Not Available	Algae or other aquatic plants	6500	0-7500mg/l	1
ethylene glycol	EC50	48h	Crustacea		0mg/l	2
	LC50	96h	Fish		000mg/l	1
	EC50	96h	Algae or other aquatic plants	6500	0-13000mg/l	1
	Endpoint	Test Duration (hr)	Species		Value	Sourc
	EC50	72h	Algae or other aquatic plants		49.3mg/l	2
ootassium 2-ethylhexanoate	EC50	48h Crustacea			85.4mg/l	2
	LC50	96h Fish			>100mg/l	2
	NOEC(ECx)	504h	Crustacea		18mg/l	2

For Surfactants: Kow cannot be easily determined due to hydrophilic/hydrophobic properties of the molecules in surfactants. BCF value: 1-350.

Aquatic Fate: Surfactants tend to accumulate at the interface of the air with water and are not extracted into one or the other liquid phases.

Terrestrial Fate: Anionic surfactants are not appreciably sorbed by inorganic solids. Cationic surfactants are strongly sorbed by solids, particularly clays. Significant sorption of anionic and non-ionic surfactants has been observed in activated sludge and organic river sediments. Surfactants have been shown to improve water infiltration into soils with moderate to severe hydrophobic or water-repellent properties.

Ecotoxicity: Some surfactants are known to be toxic to animals, ecosystems and humans, and can increase the diffusion of other environmental contaminants. The acute aquatic toxicity generally is considered to be related to the effects of the surfactant properties on the organism and not to direct chemical toxicity. Surfactants should be considered to be toxic to aquatic species under conditions that allow contact of the chemicals with the organisms. Surfactants are expected to transfer slowly from water into the flesh of fish. During this process, readily biodegradable surfactants are expected to be metabolized rapidly during the process of bioaccumulation. Surfactants are not to be considered to show bioaccumulation potential if they are readily biodegradable. DO NOT discharge into sewer or waterways.

12.2. Persistence and degradability

Ingredient	Persistence: Water/Soil	Persistence: Air	
ethylene glycol	LOW (Half-life = 24 days)	LOW (Half-life = 3.46 days)	
12.2. Piezooumulativo potential			

12.3. Bioaccumulative potential

Ingredient	Bioaccumulation
ethylene glycol	LOW (BCF = 200)

12.4. Mobility in soil

Ingredient	Mobility
ethylene glycol	HIGH (KOC = 1)

12.5. Results of PBT and vPvB assessment

	Р	В	Т
Relevant available data	Not Available	Not Available	Not Available
PBT	×	×	×
vPvB	×	×	×
PBT Criteria fulfilled? No			No
vPvB			No

12.6. Endocrine Disruption Properties

Not Available

12.7. Other adverse effects

Not Available

SECTION 13 Disposal considerations

13.1. Waste treatment methods		
Product / Packaging disposal	Legislation addressing waste disposal requirements may differ by country, state and/ or territory. Each user must refer to laws operating in their area. In some areas, certain wastes must be tracked. A Hierarchy of Controls seems to be common - the user should investigate:	

	 Reduction Reuse Recycling Disposal (if all else fails) This material may be recycled if unused, or if it has not been contaminated so as to make it unsuitable for its intended use. If it has been contaminated, it may be possible to reclaim the product by filtration, distillation or some other means. Shelf life considerations should also be applied in making decisions of this type. Note that properties of a material may change in use, and recycling or reuse may not always be appropriate. DO NOT allow wash water from cleaning or process equipment to enter drains. It may be necessary to collect all wash water for treatment before disposal. In all cases disposal to sever may be subject to local laws and regulations and these should be considered first. Where in doubt contact the responsible authority. Recycle wherever possible or consult manufacturer for recycling options. Consult State Land Waste Management Authority for disposal. Bury residue in an authorised landfill. Recycle containers if possible, or dispose of in an authorised landfill.
Waste treatment options Sewage disposal options	Not Available

SECTION 14 Transport information

Labels Required

Marine Pollutant	NO
HAZCHEM	Not Applicable

Land transport (ADR): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

14.1. UN number	Not Applicable				
14.2. UN proper shipping name	Not Applicable	Not Applicable			
14.3. Transport hazard class(es)	ClassNot ApplicableSubriskNot Applicable				
14.4. Packing group	Not Applicable				
14.5. Environmental hazard	Not Applicable				
	Hazard identification (Kemler)	Not Applicable			
	Classification code	Not Applicable			
14.6. Special precautions for	Hazard Label	Not Applicable			
user	Special provisions	Not Applicable			
	Limited quantity	Not Applicable			
	Tunnel Restriction Code	Not Applicable			

Air transport (ICAO-IATA / DGR): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

	-				
14.1. UN number	Not Applicable	Not Applicable			
14.2. UN proper shipping name	Not Applicable				
14.3. Transport hazard	ICAO/IATA Class	Not Applicable			
class(es)	ICAO / IATA Subrisk Not Applicable				
	ERG Code Not Applicable				
14.4. Packing group	Not Applicable				
14.5. Environmental hazard	Not Applicable				
14.6. Special precautions for user	Special provisions		Not Applicable		
	Cargo Only Packing Instructions		Not Applicable		
	Cargo Only Maximum Qty / Pack		Not Applicable		
	Passenger and Cargo Packing Instructions		Not Applicable		
	Passenger and Cargo Maximum Qty / Pack		Not Applicable		
	Passenger and Cargo	Limited Quantity Packing Instructions	Not Applicable		
	Passenger and Cargo Limited Maximum Qty / Pack		Not Applicable		

Sea transport (IMDG-Code / GGVSee): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

14.1. UN number	Not Applicable
14.2. UN proper shipping name	Not Applicable

14.3. Transport hazard	IMDG Class	Not Applicable
class(es)	IMDG Subrisk	Not Applicable
14.4. Packing group	Not Applicable	
14.5. Environmental hazard	Not Applicable	
14.6. Special precautions for user	EMS Number Special provisions Limited Quantities	

Inland waterways transport (ADN): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

14.1. UN number	Not Applicable
14.2. UN proper shipping name	Not Applicable
14.3. Transport hazard class(es)	Not Applicable Not Applicable
14.4. Packing group	Not Applicable
14.5. Environmental hazard	Not Applicable
14.6. Special precautions for user	Classification codeNot ApplicableSpecial provisionsNot ApplicableLimited quantityNot ApplicableEquipment requiredNot ApplicableFire cones numberNot Applicable

14.7. Transport in bulk according to Annex II of MARPOL and the IBC code

Not Applicable

14.8. Transport in bulk in accordance with MARPOL Annex V and the IMSBC Code

Product name	Group
ethylene glycol	Not Available
potassium 2-ethylhexanoate	Not Available

14.9. Transport in bulk in accordance with the ICG Code

Product name	Ship Type
ethylene glycol	Not Available
potassium 2-ethylhexanoate	Not Available

SECTION 15 Regulatory information

15.1. Safety, health and environmental regulations / legislation specific for the substance or mixture

ethylene glycol is found on the following regulatory lists

Chemical Footprint Project - Chemicals of High Concern List Great Britain GB mandatory classification and labelling list (GB MCL) UK REACH grandfathered registrations notified substances list UK Workplace Exposure Limits (WELs).

potassium 2-ethylhexanoate is found on the following regulatory lists

UK REACH grandfathered registrations notified substances list

This safety data sheet is in compliance with the following EU legislation and its adaptations - as far as applicable - : Directives 98/24/EC, - 92/85/EEC, - 94/33/EC, - 2008/98/EC, - 2010/75/EU; Commission Regulation (EU) 2020/878; Regulation (EC) No 1272/2008 as updated through ATPs.

Information according to 2012/18/EU (Seveso III):

Seveso Category Not Available

15.2. Chemical safety assessment

No Chemical Safety Assessment has been carried out for this substance/mixture by the supplier.

ECHA SUMMARY

Ingredient	CAS number Inde	ex No	ECHA Dossier	
ethylene glycol	107-21-1* 603	107-21-1* 603-027-00-1		
Harmonisation (C&L Inventory)	Hazard Class and Category Code(s)	Pictograms Signal Word Code(s)	Hazard Statement Code(s)	
1	Acute Tox. 4	GHS07; Wng	H302	
2	Acute Tox. 4; STOT RE 1; STOT SE 3; Skin Irrit. 2; E STOT SE 1; Muta. 1B; Repr. 1B; Aquatic Chronic 3	Eye Irrit. 2; GHS08; Dgr	H302; H372; H336; H319; H335; H370; H332; H340; H360; H412; H315	

Harmonisation Code 1 = The most prevalent classification. Harmonisation Code 2 = The most severe classification.

Issue Date: 12/01/2023 Print Date: 12/01/2023

HyperDrive Long-Life Antifreeze Concentrate (Purple)

Ingredient	CAS number	Index No	0	ECI	HA Dossier
potassium 2-ethylhexanoate	3164-85-0*	Not Avai	lable	Not	Available
Harmonisation (C&L Inventory)	Hazard Class and Category Code(s)		Pictograms Signal Word Code(s)		Hazard Statement Code(s)
1	Skin Irrit. 2; Eye Irrit. 2		GHS07; Wng		H315; H319
2	Skin Irrit. 2; Eye Dam. 1; Repr. 2; Aquatic Chronic	с 3	GHS08; GHS05; Dgr; GHS02		H315; H318; H412; H226; H373; H361fd

National Inventory Status

National Inventory	Status
Australia - AIIC / Australia Non-Industrial Use	Yes
Canada - DSL	Yes
Canada - NDSL	No (ethylene glycol; potassium 2-ethylhexanoate)
China - IECSC	Yes
Europe - EINEC / ELINCS / NLP	Yes
Japan - ENCS	Yes
Korea - KECI	Yes
New Zealand - NZIoC	Yes
Philippines - PICCS	Yes
USA - TSCA	Yes
Taiwan - TCSI	Yes
Mexico - INSQ	Yes
Vietnam - NCI	Yes
Russia - FBEPH	No (potassium 2-ethylhexanoate)
Legend:	Yes = All CAS declared ingredients are on the inventory No = One or more of the CAS listed ingredients are not on the inventory. These ingredients may be exempt or will require registration.

SECTION 16 Other information

Revision Date	12/01/2023
Initial Date	31/12/2022

Full text Risk and Hazard codes

H226	Flammable liquid and vapour.
H315	Causes skin irritation.
H318	Causes serious eye damage.
H332	Harmful if inhaled.
H335	May cause respiratory irritation.
H336	May cause drowsiness or dizziness.
H340	May cause genetic defects.
H360	May damage fertility or the unborn child.
H361d	Suspected of damaging the unborn child.
H361fd	Suspected of damaging fertility. Suspected of damaging the unborn child.
H370	Causes damage to organs.
H372	Causes damage to organs through prolonged or repeated exposure.
H412	Harmful to aquatic life with long lasting effects.

Other information

Classification of the preparation and its individual components has drawn on official and authoritative sources as well as independent review by the Chemwatch Classification committee using available literature references.

The SDS is a Hazard Communication tool and should be used to assist in the Risk Assessment. Many factors determine whether the reported Hazards are Risks in the workplace or other settings. Risks may be determined by reference to Exposures Scenarios. Scale of use, frequency of use and current or available engineering controls must be considered. For detailed advice on Personal Protective Equipment, refer to the following EU CEN Standards:

EN 166 Personal eye-protection

EN 340 Protective clothing

EN 374 Protective gloves against chemicals and micro-organisms

EN 13832 Footwear protecting against chemicals

EN 133 Respiratory protective devices

Definitions and abbreviations

PC-TWA: Permissible Concentration-Time Weighted Average

PC-STEL: Permissible Concentration-Short Term Exposure Limit

IARC: International Agency for Research on Cancer

ACGIH: American Conference of Governmental Industrial Hygienists STEL: Short Term Exposure Limit

TEEL: Temporary Emergency Exposure Limit。

IDLH: Immediately Dangerous to Life or Health Concentrations ES: Exposure Standard OSF: Odour Safety Factor NOAEL :No Observed Adverse Effect Level LOAEL: Lowest Observed Adverse Effect Level TLV: Threshold Limit Value LOD: Limit Of Detection OTV: Odour Threshold Value BCF: BioConcentration Factors BEI: Biological Exposure Index AIIC: Australian Inventory of Industrial Chemicals DSL: Domestic Substances List NDSL: Non-Domestic Substances List IECSC: Inventory of Existing Chemical Substance in China EINECS: European INventory of Existing Commercial chemical Substances ELINCS: European List of Notified Chemical Substances NLP: No-Longer Polymers ENCS: Existing and New Chemical Substances Inventory KECI: Korea Existing Chemicals Inventory NZIoC: New Zealand Inventory of Chemicals PICCS: Philippine Inventory of Chemicals and Chemical Substances TSCA: Toxic Substances Control Act TCSI: Taiwan Chemical Substance Inventory INSQ: Inventario Nacional de Sustancias Químicas NCI: National Chemical Inventory FBEPH: Russian Register of Potentially Hazardous Chemical and Biological Substances

Powered by AuthorITe, from Chemwatch.

